



MARTINAL[®] TM-3719

Aluminum Hydroxide

Einsatzbeispiele / Applications

MARTINAL TM-3719 ist ein beschichtetes, wärmeleitendes Material, das für sich allein oder in Kombination mit anderen Füllstoffen verwendet werden kann. Die Beschichtung ermöglicht höchste Füllgrade in Epoxidharzen, Polyurethansystemen und Silikon.

MARTINAL TM-3719 is a surface treated thermally conductive material designed to be used either by itself or in blends with other fillers to attain highest loadings in epoxy, polyurethane and silicone based gap fillers.

Durchschnittsanalyse / Typical analysis

| | | |
|---|-----------------------|--------|
| Al(OH) ₃ -Gehalt /-content | [%] | ≈ 99.6 |
| Feuchte / Moisture (105 °C) | [%] | ≤ 0.25 |
| Glühverlust / Loss on Ignition (1200 °C) | [%] | ≈ 34.5 |
| Na ₂ O löslich / soluble | [%] | ≤ 0.30 |
| Brechungsindex / Refractive index | [%] | 1.58 |
| Teilchengröße (Laserbeugung, Cilas) / Particle Size (Laser scattering, Cilas) | | |
| | d ₉₀ [μm] | < 50 |
| | d ₁₀₀ [μm] | < 100 |
| Dichte / Density | [g/cm ³] | 2.4 |
| Schüttdichte / Bulk Density | [kg/m ³] | ≈ 1000 |

Shipping Information

Packaging and minimum order quantity information is available from sales or customer service.

Safety and Handling Information

For specific safety, toxicity and handling information, please refer to the material safety data sheet on this product.

Chemical Registration Numbers

Chem. Bezeichnung / Chem. name: Aluminum Hydroxide
Formel / formula: $\text{Al}(\text{OH})_3$
CAS No.: 21645-51-2
EC/EINECS No.: 244-492-7

EUROPE, MIDDLE EAST, AFRICA

Martinswerk GmbH
Kölner Straße 110
D-50127 Bergheim

Phone: +49-2271-902-0
Fax: +49-2271-902-710

AMERICAS

Huber Engineered Materials
3100 Cumberland Boulevard
Suite 600
Atlanta, Georgia 30339

Phone: +1 (678) 247-7300
Fax: +1 (678) 247-2797

ASIA PACIFIC

Huber Fire Retardant Additives
(Qingdao) Co.Ltd
8th Floor No.2 Building, No.7,
Wuyishan Road, Huangdao District,
Qingdao – China

Phone: +86 532-58792008
Fax: +86 532-58792008

Web: www.huberadvancedmaterials.com
www.hubermaterials.com

Email: info@martinswerk.com
hubermaterials@huber.com



THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Martinswerk's Standard Conditions of Sale for the only express warranties applicable to the Martinswerk products. Products incorporating Martinswerk products are not warranted by Martinswerk. In no event is Martinswerk liable for consequential damages. **MARTINAL**® is used, applied for, or registered as a trademark of Martinswerk GmbH in various countries around the world.
© April 2025 Martinswerk GmbH